

Laying instructions

- For application on special surfaces, consult with Weser's technical service.
- Work at a temperature of 5 to 30 degrees.
- Use the appropriate De Ryck adhesives and installation products.
- Always use pieces from several boxes to obtain a more uniform result



The surface must be consistent, flat and clean. It must be dry and free of grease. If the surface is porous then apply first a layer of Cemix Primer. Allow to dry for 2 hours and then you can begin.



Section off the wall in areas for about five brick strips. Within these sections you can work by sight.



Apply the adhesive in sections of ½ m² so it doesn't dry before you fix the brick strips. Stains from spotting and spilling can then still be easily removed.



Start by making ribs in the glue with a notched spatula (6 mm for Interfix, 8 mm for Granulit and 10 mm for Murok).



Then apply the strip in a sliding motion. Always start with the corners and mix strips from different boxes.



For the heavier stone products of the Murok range the installation with the back-butter technique is required. This means that the glue must be applied as well on the back of the slips as on the wall-surface.



In this way you can monitor if the strips are well attached to the wall.



To size the strips as needed, saw them or notch them in the back and then break along the line.



Place cut pieces together in a way to preserve the rustic aspect.



Cladding with joints: Filling joints is done with Cemix Unijoint which is mixed with water. Fill the joints using a mortar plastic bag. Keep using the same proportion of water to avoid colour variations.



When the joint begin to harden, tighten it with a narrow trowel or simply with the wooden handle of a brush. Do not touch the joints as they are fresh and they have not sufficiently cured. If the cladding is stained by the mortar, wipe gently with a sponge soaked in water.



Clean away the extra mortar with a stiff dry brush before it has completely dried.



Interfix: the joints can be filled in the traditional manner. Or the Interfix glue can be stroked smooth in the joint. Do this with a damp finishing brush, such that the glue seals with the edge of the strip.



Outside walls should always be sealed with Silifin. The wall must be completely dry before you apply the Silifin with a brush until thoroughly covered.